


| MODELO / MODEL | | FOSEN SERIES | | |
|--|---|--|-----------------|------------------------|
| FOTO / PICTURE (ORIENTATIVE) | |  <p>P.E. FOSEN GRIS MATE 25X100 RECT. P.E. FOSEN CAMEL MATE 25X100 RECT. P.E. FOSEN CENIZA MATE 25X100 RECT.</p> <p>P.E. FOSEN NATURAL MATE 25X100 RECT.</p> | | |
| FORMATO / SIZE | | 25X100 cms. RECT. | | |
| GRUPO / GROUP | | Bla | | |
| TIPO / TYPE | | PORCELANICO ESMALTADO / Glazed Porcelain Tile | | |
| DESCRIPCION DEL TEST / TEST DESCRIPTION | | VALOR DEL TEST / TEST VALUE | KERATILE | NORMA / STANDARD |
| ABSORCIÓN DE AGUA / WATER ABSORPTION | | AA < 0,5% | Cumple / Passed | UNE-EN-ISO 10545-3 |
| FUERZA DE ROTURA / BREAKING STRENGTH | | > 1300 N | Cumple / Passed | UNE-EN-ISO 10545-4 |
| RESISTENCIA A LA FLEXIÓN / RESISTANCE OF FLEXION | | > 35 N/mm2 | Cumple / Passed | UNE-EN-ISO 10545-4 |
| ABRASION SUPERFICIAL / SURFACE ABRASION | | Clase / Class | PEI III | UNE-EN-ISO 10545-7 |
| RESISTENCIA AL CUARTEO / CRACKING RESISTANCE | | Requerido / Requested | Cumple / Passed | UNE-EN-ISO 10545-11 |
| RESISTENCIA A LA HELADA / FROST RESISTANCE | | Requerido / Requested | Cumple / Passed | UNE-EN-ISO 10545-12 |
| RESISTENCIA QUIMICA / CHEMICAL RESISTANCE | (PRODUCTOS DOMESTICOS Y DE PISCINA / Domestic & Swimming Pool Products) | Mínimo / Minimum GB | Cumple / Passed | UNE-EN-ISO 10545-13 |
| RESISTENCIA A LOS ACIDOS / ACID RESISTANCE | | GHA | Cumple / Passed | UNE-EN-ISO 10545-13 |
| RESISTENCIA A LAS BASES / ALKALINE RESISTANCE | | GHA | Cumple / Passed | UNE-EN-ISO 10545-13 |
| RESISTENCIA A LAS MANCHAS / RESISTANCE TO STAINS | | Mínimo / Minimum Class 3 | Cumple / Passed | UNE-EN-ISO 10545-14 |
| RESISTENCIA AL DESLIZAMIENTO / SLIP RESISTANCE | | Metodo Disponible / Available Method | Class 1 | UNE-ENV 12633:2003 |
| SLIP RESISTANCE | | D.C.O.F. | >0,42 | ANSI A137. 1:2012. 9.6 |
| RESISTENCIA AL RAYADO / HARDNESS (MOHS) | | Mínimo / Minimum 3 | Cumple / Passed | EN 101 |